



## INTERNATIONAL TESTING CENTRE

# TEST CERTIFICATE

Customer Name : Yaqoob Tanners. Test report No. : 2K2312270-1  
 Contact person : Mr. Date of Entry : 23.12.2023  
 Address : 67/8, Pokharpur, K.D.A. Colony, Jajmau, Kanpur (U.P.) - 208010  
 Sample description: Safety Shoe (Size – 8) Page : 1/1  
 Details : Article – Supreme (Single Density) , Brand:- Zain  
 Specification : IS - 15298 (P-2) : 2016, Classification - I  
 Testing period : 26.12.2023 to 08.01.2024 Reporting date : 08.01.2024

Laboratory Environment  
 Temperature 27 +/-2°C  
 Relative Humidity 65 +/-5%  
 The sample was conditioned for 48 hours

S.No.	Test Name	Clause	Value	Requirement	Conformity
<b>1. Test on Whole Footwear (5.3)</b>					
a.	Upper/Outsole bond	5.3.1.2	4.8 N/mm	4 N/mm (minimum)	Conforms
b.	Impact resistance – 200 J	5.3.2.3	18.0 mm No crack was observed.	14.0 mm (min.), toecap shall not develop any cracks on the test axis.	Conforms
c.	Compression resistance- 15 kN	5.3.2.4	20.0 mm	14.0 mm (min.)	Conforms
d.	Slip resistance – 5.3.5 (SRC)	5.3.5.4	0.30 0.39 0.14 0.18	Coefficient of friction for Condition A(Forward heel slip)≥0.28 Condition B(Forward flat slip)≥0.32 Condition C(Forward heel slip)≥0.13 Condition D(Forward flat slip)≥0.18	Conforms
e.	Antistatic Test	6.2.2.2	Dry : 893 M Ohm Wet : 350 M Ohm	100 k Ohm – 1000 M Ohm	Conforms
<b>2. Test on Upper (5.4)</b>					
a.	Tear strength	5.4.3	309 N	120 N (minimum)	Conforms
b.	Tensile strength	5.4.4	46.8 N/mm <sup>2</sup>	15 N/mm <sup>2</sup> (minimum)	Conforms
<b>3. Test on Sole – 5.8</b>					
a.	Abrasion resistance	5.8.3	94 mm <sup>3</sup>	250 mm <sup>3</sup> (max.) density ≤ 0.9g/cm <sup>3</sup>	Conforms

**Rajesh Mishra**  
 (Senior Technologist)  
 Authorized signatory



**Shailendra Saxena**  
 (Head -Physical Laboratory)  
 Authorized signatory

\*\*\*END OF TEST REPORT\*\*\*

1. This report is for technical information of the client only. Not for advertisement, promotion, publicity litigation or legal purpose.
2. This institute shall be indemnified against any dispute arising out of issue of this report.
3. Sample not drawn by FDDI and the test results relate only to the material tested.
4. The report must not be reproduced except in full without approved of FDDI.

**FOOTWEAR DESIGN & DEVELOPMENT INSTITUTE**  
 MINISTRY OF COMMERCE & INDUSTRY, GOVERNMENT OF INDIA